

Designed for Roofing Installation & Repair

ROOF CEMENT *Sealant*

Stops Roof Leaks / All-Weather Formula / Resists Cracking

Titebond® Roof Cement Sealant is an all-weather, asphalt-based patching compound specifically designed and formulated to repair cracks, seams, gaps and holes in roofing materials. This sealant is ideal for repair and new construction roofing applications. It is used to set flashings, drip edges and roofing material edges as well as the installation of shingles and roll roofing.

WET OR DRY CONDITIONS

Ideal For

Sealing around Skylights, Vents, Chimneys, Valleys & Exhaust Pipes / Flashings / Drip Edges / General Roofing Repair / Repair Roof Cracks and Holes

Seals

Metal / Aluminum / Asphalt / Shingles / Masonry / Wood / Most Common Building Materials

VOC Compliant

VOC-compliant in all 50 states

Joint Movement

Remains flexible

Weather Resistant

Produces long-lasting weather-tight seals

Wide Temperature Application Range

50°F - 120°F



Titebond®
THE PRO'S ADVANTAGE

Ordering/Sku Information

Size/Color	Part Number	UPC	Case UPC	Weight	Units Per Package	Packages Per Pallet
10.3 Oz. Cartridge / Black	3211	037083032116	10037083032113	10.18 lbs.	12	108

Physical & Chemical Properties

- **Type:** Asphalt
- **Calculated VOC:** 300 g/L (27%)
- **Tooling time:** 10-20 minutes
- **Full cure:** 3-7 days*
- **Freeze thaw stability:** Will not freeze
- **Flashpoint:** >105°F
- **Application temperature:** Above 50°F (10°C)
- **Joint movement capability:** Remains flexible
- **Storage life:** 12 months in a dry location at or below 75°F
- **Coverage:** 32 linear ft. at a 1/4" bead
- **Tack-free time:** 8 hours
- **Solids:** 75%-80%
- **Cleanup:** Clean uncured material with xylene or equivalent solvent. Follow solvent vendor's precautions when using solvents.

* Cure will be affected by joint size, configuration and environmental conditions.

Specifications

Complies with the following requirements:

- Federal Specification SS-S-153C Type I
- ASTM D6511
- SCAQMD Rule #1168
- ASTM D4586

Application

Titebond® Roof Cement Sealant comes ready to use. Surfaces must be clean and free of any material that may prevent adequate adhesion. Cut tip to desired bead width and shape and place in professional cartridge gun. Apply generously as needed. It is the sole responsibility of the user to thoroughly test any proposed use with all substrates to determine project suitability.

Limitations

Air, sealant and surface temperature should be above 50°F. In colder weather (50°F and below) product should be stored inside between 70°F and 80°F for 24 hours prior to application. Cure time is dependent upon ambient conditions including temperature and humidity. The sealant should be dry to the touch in 2 hours. Allow product to cure between 30 and 60 days prior to application of reflective coating. Do not thin. **DO NOT APPLY DIRECTLY TO HEAT/FLAMES.** Do not apply to plastic, EPDM, Hypalon or similar type of synthetic rubber roof systems. If there is a question on compatibility, test a small area first before application to entire surface area. For best results, store in a dry location at or below 75°F. For questions, please call our Help Line 1.800.347.4583 or visit us at Titebond.com.

Liability is limited to product replacement only.

Visit Titebond.com for the most up-to-date product information.

Franklin International



Columbus, Ohio 43207 614.443.0241 Technical Service 1.800.347.4583 © 2021 01592_5435LN FF1025

